

Filter stable drainage systems

Secudrain® WD



NAUE GmbH & Co. KG
Gewerbestr. 2
32339 Espelkamp – Fiestel
Germany

Phone: +49 57 43 – 41 - 0
Fax: +49 57 43 – 41 - 240

info@naue.com

www.naue.com

Product description

Double- or three-layered, three-dimensional, filter stable and high compression resistance drainage systems consisting of an extruded wave-shaped monofilament core and a needle-punched nonwoven fully bonded at least on one side

Property	Test method*	Unit	201 WD 601	201 WD 601 201
Total product	-	-		
Water flow rate $q_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa	EN ISO 12958	l/(m x s)	<i>i</i> = 0.1 $1.0 \times 10^{+0}$	<i>i</i> = 0.1 5.0×10^{-1}
Water flow rate $q_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa			<i>i</i> = 0.1 8.0×10^{-1}	<i>i</i> = 0.1 4.0×10^{-1}
Water flow rate $q_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa			<i>i</i> = 0.3 $2.0 \times 10^{+0}$ <i>i</i> = 0.3 $1.5 \times 10^{+0}$	<i>i</i> = 0.3 9.0×10^{-1} <i>i</i> = 0.3 8.0×10^{-1}
Water flow rate $q_{(h/h)}$ - at a load of 20 kPa - at a load of 50 kPa			<i>i</i> = 1.0 $4.0 \times 10^{+0}$ <i>i</i> = 1.0 $3.0 \times 10^{+0}$	<i>i</i> = 1.0 $2.0 \times 10^{+0}$ <i>i</i> = 1.0 $1.5 \times 10^{+0}$
Mass per unit area	EN ISO 9864	g/m ²	800	1,000
Thickness	EN ISO 9863-1	mm	approx. 11.0	approx. 12.0
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	8.0 / 14.0	16.0 / 24.0
Elongation at max. tensile strength, md / cmd**	EN ISO 10319	%	50 / 40	50 / 40
Puncture force	EN ISO 12236	kN	2.0	3.8
Raw material	-	-	polypropylene	
Geotextiles	201 (/ 201)	-		
Mass per unit area	EN ISO 9864	g/m ²	200	
Thickness	EN ISO 9863-1	mm	2.5	
Characteristic Opening Size	EN ISO 12956	mm	0.12	
Water permeability - $V_{I_{H50}}$ -Index - Flow rate $_{H50}$	EN ISO 11058	m/s	1.0×10^{-1}	
		l/sm ²	100	
Roll dimension, width x length	-	m x m	3.80 / 1.90 x 35	

*based on, **md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.